

**full bed  
mosaic.**



Getty Grey® 4"-6" mosaic



Montville® 4"-6" mosaic

**thin  
wall.**



Getty Grey® 1"-3" thin wall



Montville® 1"-3" thin wall

**bulk  
stone.**



Getty Grey®



Montville®

PRODUCT SPECIFICATIONS

TABLE OF DIMENSION STONE TESTING VALUES PER ASTM STANDARD	ABSORPTI ON (MAX) ASTM C97	DENSITY (MIN) ASTM C97		MODULUS OF RUPTURE (MIN) ASTM C99 (9) (10)		COMPREHENSIVE STRENGTH (MIN) ASTM C170		ABRASION RESISTANCE (MIN) ASTM C241	FLEXURAL STRENGTH (MIN) ASTM C880	
	%	LBS/FT <sup>3</sup>	KG/M <sup>3</sup>	LBS/IN <sup>2</sup>	MPA	LBS/IN <sup>2</sup>	MPA	H <sub>2</sub>	LBS/IN <sup>2</sup>	MPA
<b>ASTM STANDARD</b>	0.40%	160	2.56	1500	10.34	19,000	131	25	1,200	8.27
<b>GETTY GREY™</b>	0.10%	178.5	2.859	*3761.5	25.93	21,700	149.62	N/A	*3454	23.81
<b>MONTVILLE™</b>	0.26%	163.4	2.617	*3720.25	25.65	24,750	170.65	N/A	*2882.75	19.88

\* AVERAGE OF DRY & WET TESTS

VENEER TYPE	BED DEPTH	AVG. COVERAGE*	FACING AREA	SOLD BY
MOSAIC	± 4" - ± 6"	±30-35 SF PER TON	± ¼ SF to ± 3 SF	TON
THIN WALL	± 1" - ± 3"	±12-14 CF PER TON	± ¼ SF to ± 1 SF	TON
IRREGULAR FLAGGING	± 2" - ± 3"	±55-60 SF PER TON	± 2 - ± 9 SF	TON
IRREGULAR STEPS	± 6" - ± 12"	N/A	VARIOUS	TON

MATERIAL COVERAGE IS EXCLUSIVE OF ANY WASTE. ASSUME A MINIMUM 10% TO 15% WASTE FACTOR.

**GETTY GRANITE**

a division of Connecticut Superior Stone  
gettygranite.com